

APPARATUS FOR PRODUCING AIR-CUSHIONINH MATERIAL AND THE MATERIAL

Patent number: WO03106137

Publication date: 2003-12-24

Inventor: MITSUDA TERUO (JP); ISHIDA MITSUO (JP); SHIBUTANI MASAHIRO (JP)

Applicant: SHINWA CORP (JP); MITSUDA TERUO (JP); ISHIDA MITSUO (JP); SHIBUTANI MASAHIRO (JP)

Classification:

- international: *B29C47/00; B29C47/20; B65D81/09; B29C47/00; B29C47/20; B65D81/05; (IPC1-7): B29C47/00; B29C47/12; B65D81/02*

- european: B29C47/00D2; B29C47/20E; B65D81/09

Application number: WO2003JP07162 20030605

Priority number(s): JP20020170290 20020611; JP20030072177 20030317; JP20030149233 20030527

Also published as:



JP2004338793 (A)

AU2003242198 (A1)

Cited documents:



JP2001139004

JP2000053166

JP2002255247

EP0798231


JP8324643

more >>

Report a data error here

Abstract of WO03106137

An air-cushioning material and an apparatus for producing the material, where the material is capable of reliably preventing a product or a part from being broken or deformed. An air-cushioning material-producing apparatus produces an air-cushioning material in the following way. Molten resin is sent out from a resin melting/extruding apparatus (51) through a hose (53) provided with a heater, and compressed air is sent out by a hose (54). A resin hollow-cylindrical body is formed by discharging molten resin from a resin discharge opening (58) where four adjacent closed loops are formed in a molten resin discharge member (57) of an air-cushioning material-forming machine (55). One end of the hollow-cylindrical body is cooled in a cooling section (60) and pressed and sealed by a press member (61) so as to form a resin hollow-cylindrical body having the bottom. Compressed air is blown from an air blow-out/exhaust opening (59) provided at a position surrounded by the closed loop-like resin discharge opening (58) so that the resin hollow-cylindrical body is made to contain air inside. The other end is pressed and sealed by the press member (61) while extra air in the resin hollow-cylindrical body is being exhausted from the air blow-out/exhaust opening (59). In this way, an air-cushioning material (10) having sealed both ends (12a, 12b) and adjacent four air cells (11) is produced.



Data supplied from the esp@cenet database - Worldwide